

The listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended) A method for fabricating a semiconductor film comprising:

irradiating a semiconductor film formed over a substrate with a laser beam to crystallize the semiconductor film,

wherein ultrasonic vibration is applied to the substrate during irradiating the laser beam while floating the substrate and holding an end portion of the substrate.

2. (Original) A method for fabricating a semiconductor film according to claim 1, wherein said laser beam is a YVO₄, a YAG, a YLF or an excimer laser.

3. (Original) A method for fabricating a semiconductor film comprising:

holding a substrate over a stage having pores wherein said substrate is provided with a semiconductor film;

spouting gases from the pores to float the substrate; and

irradiating a semiconductor film formed over the substrate with a laser beam while holding an end portion of the substrate,

wherein during irradiating the laser beam, ultrasonic vibration is applied to the substrate.

4. (Original) A method for fabricating a semiconductor film according to claim 3, wherein said laser beam is a YVO₄, a YAG, a YLF or an excimer laser.

5. (Currently Amended) A method for fabricating a semiconductor device comprising:

forming a semiconductor film having an amorphous structure over a substrate;
and

irradiating the semiconductor film with a laser beam while floating the substrate
and applying ultrasonic vibration to the substrate to crystallize the semiconductor film.

6. (Original) A method for fabricating a semiconductor device according to claim
5,

wherein said laser beam is a YVO₄, a YAG, a YLF or an excimer laser.

7. (Original) A method for fabricating a semiconductor device according to claim
5,

wherein said semiconductor device is used for a display device selected from the
group consisting of a video camera, a digital camera, a goggle-type display, a
navigation system, a sound reproduction device, a lap-top personal computer, a game
machine, a portable information terminal, and an image reproduction device.

8. (Original) A method for fabricating a semiconductor device comprising:
forming a semiconductor film having an amorphous structure over a substrate;
and

irradiating the semiconductor film with a laser beam condensed into a linear
shape in an oxygen atmosphere while floating the substrate and applying ultrasonic
vibration to the substrate to crystallize the semiconductor film.

9. (Original) A method for fabricating a semiconductor device according to claim
8,

wherein said laser beam is a YVO₄, a YAG, a YLF or an excimer laser.

10. (Original) A method for fabricating a semiconductor device according to claim 8,

wherein said semiconductor device is used for a display device selected from the group consisting of a video camera, a digital camera, a goggle-type display, a navigation system, a sound reproduction device, a lap-top personal computer, a game machine, a portable information terminal, and an image reproduction device.

11. (Currently Amended) A method for fabricating a semiconductor device comprising:

forming a semiconductor film having an amorphous structure over a substrate;

irradiating the semiconductor film with a laser beam condensed into a linear shape while floating the substrate and applying ultrasonic vibration to the substrate to crystallize the semiconductor film; and

crystallizing a whole surface of the semiconductor film while overlapping a beam spot of the laser beam on the film.

12. (Original) A method for fabricating a semiconductor device according to claim 11,

wherein said laser beam is a YVO₄, a YAG, a YLF or an excimer laser.

13. (Original) A method for fabricating a semiconductor device according to claim 11,

wherein said semiconductor device is used for a display device selected from the group consisting of a video camera, a digital camera, a goggle-type display, a navigation system, a sound reproduction device, a lap-top personal computer, a game machine, a portable information terminal, and an image reproduction device.

14. (Original) A method for fabricating a semiconductor device comprising:
forming a semiconductor film having an amorphous structure over a substrate;
crystallizing the semiconductor film having an amorphous structure by adding a metal element or a metal compound having catalytic action for enhancing a crystallization of the semiconductor film and by heat-treating; and
irradiating the semiconductor film with a laser beam condensed into a linear shape while floating the substrate and applying ultrasonic vibration to the substrate in order to improve a crystallinity of the semiconductor film.

15. (Original) A method for fabricating a semiconductor device according to claim 14,
wherein said laser beam is a YVO₄, a YAG, a YLF or an excimer laser.

16. (Original) A method for fabricating a semiconductor device according to claim 14,
wherein said semiconductor device is used for a display device selected from the group consisting of a video camera, a digital camera, a goggle-type display, a navigation system, a sound reproduction device, a lap-top personal computer, a game machine, a portable information terminal, and an image reproduction device.

17. (Original) A method for fabricating a semiconductor device according to claim 14,
wherein said metal element is nickel or platinum.

18. (Currently Amended) A method for fabricating a semiconductor device comprising:
forming a semiconductor film having an amorphous structure over a substrate;

crystallizing the semiconductor film having the amorphous structure by adding a metal element or a metal compound having catalytic action for enhancing a crystallization of the semiconductor film and by heat-treating;

irradiating the semiconductor film with a laser beam condensed into a linear beam while floating the substrate and applying ultrasonic vibration to the substrate in order to improve a crystallinity of the semiconductor film; and

improving a crystallinity of the semiconductor film while overlapping a beam spot of the laser beam on the film.

19. (Original) A method for fabricating a semiconductor device according to claim 18,

wherein said laser beam is a YVO₄, a YAG, a YLF or an excimer laser.

20. (Original) A method for fabricating a semiconductor device according to claim 18,

wherein said semiconductor device is used for a display device selected from the group consisting of a video camera, a digital camera, a goggle-type display, a navigation system, a sound reproduction device, a lap-top personal computer, a game machine, a portable information terminal, and an image reproduction device.

21. (Original) A method for fabricating a semiconductor device according to claim 18,

wherein said metal element is nickel or platinum.

22.-25. (Canceled)